

TECHNICAL DATA SHEET

EBA 1481 - 70

I. <u>DESCRIPTION</u>

EBA 1481 - 70 is a short oil alkyd resin based on mixture of vegatable oils. It can be used for NC lacquer, acid curing and baking finishes.

II. PERFORMANCE

- Fast dry.
- Good hardness.
- Good adhesion.
- Good gloss and gloss retention.

III. SUGGESTED USES

- Amino Alkyd acid curing.
- NC lacquer.
- Baking enamel.

IV. SPECIFICATION

• Non-Volatile (150 °C, 15 mins) : $70 \pm 1 \%$

• Viscosity (25 °C, Gardner-Holdt) : Z2 - Z4 (60 % in xylene)

• Acid Value (mg KOH/g solid) : maximum 10

• Color (Gardner-Holdt) : maximum 3 (60 % in xylene)

Appearance : clean & clear
 Specific Gravity (25 °C) : ca. 1.0535
 OH Value (mg KOH/g solid) : ca. 180

V. STANDARD PACKING

200 kgs in metal drums.

VI. STORAGE AND HANDLING

- Store in proper warehouse.
- Keep container closed when not in use.

The information contained herein is correct to the best of our knowledge. The recommendations or suggestions contained in this bulletin are made without guarantee or representation as to results. We suggest that you evaluate these recommendations and suggestions in your own laboratory prior to use. Our responsibility for claims arising from breach of warranty, negligence or otherwise is limited to the purchase price of the material.

 PT. ETERNAL BUANA CHEMICAL INDUSTRIES
 Issue date
 : Jan 10, 1996

 Tel. (62-21) 571 2998, Fax : (61-21) 571 2678
 Revised no
 : 01

 Revised date
 : June 01, 2001