

**TECHNICAL DATA SHEET****EBA 1531 - 70 EC****I. DESCRIPTION**

EBA 1531 - 70 EC is rosin-phenolic modified alkyd. It is designed especially for corrosion resistant primers and also can be used for hammer finishes.

II. PERFORMANCE

- Fast dry.
- Good hardness and adhesion.
- Anti corrosion.

III. SUGGESTED USES

- Corrosion resistant primers.

IV. SPECIFICATION

- Non-Volatile (150 °C, 15 mins) : 70 ± 1 %
- Viscosity (25 °C, Gardner-Holdt) : Y - Z (50 % in xylene)
- Acid Value (mg KOH/g solid) : 18 - 34
- Color (Gardner-Holdt) : maximum 10 (50 % in xylene)
- Appearance : clean & clear
- Specific Gravity (25 °C) : ca. 1.056

V. STANDARD PACKING

200 kgs in metal drums.

VI. STORAGE AND HANDLING

- Store in proper warehouse.
- Keep container closed when not in use.

The information contained herein is correct to the best of our knowledge. The recommendations or suggestions contained in this bulletin are made without guarantee or representation as to results. We suggest that you evaluate these recommendations and suggestions in your own laboratory prior to use. Our responsibility for claims arising from breach of warranty, negligence or otherwise is limited to the purchase price of the material.