

**TECHNICAL DATA SHEET****EBA 1532 - 50 HV****I. DESCRIPTION**

EBA 1532 - 50 HV is a rosin - petrosin - phenolic modified alkyd with superior in drying time and excellent hardness. It can be used for metal primers for industrial paint.

II. PERFORMANCE

- Fast dry.
- Good water resistance.
- High viscosity.

III. SUGGESTED USES

- Metal primers for industrial paint.

IV. SPECIFICATION

- Non-Volatile (150 °C, 15 mins) : 50 ± 1 %
- Viscosity (25 °C, Gardner-Holdt) : Z2 - Z3
- Acid Value (mg KOH/g solid) : 15 - 25
- Color (Gardner-Holdt) : maximum 12
- Appearance : clear & clean
- Specific Gravity (25 °C) : ca. 0.926

V. STANDARD PACKING

195 kgs in metal drums.

VI. STORAGE AND HANDLING

- Store in proper warehouse.
- Keep container closed when not in use.

The information contained herein is correct to the best of our knowledge. The recommendations or suggestions contained in this bulletin are made without guarantee or representation as to results. We suggest that you evaluate these recommendations and suggestions in your own laboratory prior to use. Our responsibility for claims arising from breach of warranty, negligence or otherwise is limited to the purchase price of the material.