

**TECHNICAL DATA SHEET****EBINO 8313 - 60****I. DESCRIPTION**

EBINO 8313 - 60 is n-butylated urea melamine formaldehyde resin. In combination with short oil alkyd resin, it is mainly used for wood finishes. It is designed to give low odor resin and high viscosity.

II. PERFORMANCE

- Low odor.
- High viscosity.
- Gloss.

III. SUGGESTED USES

- Acid curing amino - alkyd.

IV. SPECIFICATION

- Non-Volatile (150 °C, 15 mins) : 60 ± 2 %
- Viscosity (25 °C, Gardner - Holdt) : Z1 - Z3
- Acid Value (mg KOH/g solid) : maximum 4
- Color (Gardner-Holdt) : maximum 1
- Appearance : clean & clear
- Free Formaldehyde : maximum 1.10 %
- Specific Gravity (25 °C) : ca. 1.022

V. STANDARD PACKING

210 kgs in metal drums.

VI. STORAGE AND HANDLING

- Store in proper warehouse.
- Keep container closed when not in use.

The information contained herein is correct to the best of our knowledge. The recommendations or suggestions contained in this bulletin are made without guarantee or representation as to results. We suggest that you evaluate these recommendations and suggestions in your own laboratory prior to use. Our responsibility for claims arising from breach of warranty, negligence or otherwise is limited to the purchase price of the material.