: Jan 10, 1996

: June 01, 2001

Revised date



TECHNICAL DATA SHEET

EBL - 3307

I. DESCRIPTION

EBL - 3307 is a milky white synthetic resin of Polyvinyl Versatate Copolymer specially designed for making high quality exterior and interior emulsion paint.

II. PERFORMANCE

- Excellent durability.
- High pigment loading.
- Excellent water resistance.
- Excellent alkaly resistance.

III. SPECIFICATION

Non-Volatile (150 °C, 15 mins) : 50 ± 1 %
 Viscosity at 30 °C, cPs : 1,000 - 2,500 (Brookfield LVT, No.4/60 rpm)

• pH Value : 4 - 5

Appearance : Milky White
Density, lbs./US gallon : 8.80 - 9.95
Dry film : C.Transparent
Mechanical stability : Very good
Chemical stability : Very good
Toxicity : Non toxic
Theoretical Tg, °C : + 21

IV. STANDARD PACKING

200 kgs in open head metal drums packed inside with 2 liners of HDPE plastic bags.

V. STORAGE

- Avoid direct sunlight.
- Keep the plastic bags for remaining stock tightly sealed to avoid skinning.

The information contained herein is correct to the best of our knowledge. The recommendations or suggestions contained in this bulletin are made without guarantee or representation as to results. We suggest that you evaluate these recommendations and suggestions in your own laboratory prior to use. Our responsibility for claims arising from breach of warranty, negligence or otherwise is limited to the purchase price of the material.

PT. ETERNAL BUANA CHEMICAL INDUSTRIES

Tel. (62-21) 571 2998, Fax: (61-21) 571 2678

Issue date
Revised no



TECHNICAL DATA SHEET

• Storage life is 6 months after delivery.

The information contained herein is correct to the best of our knowledge. The recommendations or suggestions contained in this bulletin are made without guarantee or representation as to results. We suggest that you evaluate these recommendations and suggestions in your own laboratory prior to use. Our responsibility for claims arising from breach of warranty, negligence or otherwise is limited to the purchase price of the material.

PT. ETERNAL BUANA CHEMICAL INDUSTRIES Tel. (62-21) 571 2998, Fax: (61-21) 571 2678 Issue date : Jan 10, 1996 Revised no : 01

Revised date : June 01, 2001