



TECHNICAL DATA SHEET

EBL - 7852 A

I. DESCRIPTION

EBL - 7852 A is a Vinyl Acetate-Acrylic Copolymer with a record of outstanding performance in latex house paints.

II. PERFORMANCE

- Good adhesion.
- Wide tolerance.

III. SPECIFICATION

- Non-Volatile (150 °C, 15 mins) : 58 ± 1 %
- Viscosity at 30 °C, cPs : 3,000 - 5,000
(Brookfield LVT, No.4/60 rpm)
- pH Value : 4 - 5
- Appearance : Milky White
- Density, (30 °C), gr/cm³ : 1.03 - 1.18
- Particle Size, Mastersizer/E micron : 0.3 - 0.5
- Free Monomer, % : 0.35 %
- Theoretical Tg, °C : + 10
- Toxicity : Non Toxic
- Ionic Nature : Anionic
- Weight per gallon at 20 °C
 - Latex : 9.02 lb
 - Solid : 9.65 lb
- Specific Gravity at 20/20 °C
 - Latex : 1.08
 - Solid : 1.16
- Surface Tension of latex : 38 dyne/cm
- Stability in the presence of :

The information contained herein is correct to the best of our knowledge. The recommendations or suggestions contained in this bulletin are made without guarantee or representation as to results. We suggest that you evaluate these recommendations and suggestions in your own laboratory prior to use. Our responsibility for claims arising from breach of warranty, negligence or otherwise is limited to the purchase price of the material.



TECHNICAL DATA SHEET

Borax	: Excellent
Basic Silicate of Lead	: Excellent
Electrolytes	: Excellent
Mechanical Stability of Latex	: Excellent
Water- resistance of film	: Excellent
Alkali-resistance of film	: Excellent
Freeze Thaw Stability :	
Gel Condition	: c.a 0.1%
Forming Agglomeration	: c.a 0.1%
Increase of Viscosity	: c.a 200 cPs

IV. STANDARD PACKING

200 kgs in open head metal drums packed inside with 2 liners of HDPE plastic bags.

V. STORAGE

- Avoid direct sunlight.
- Keep the plastic bags for remaining stock tightly sealed to avoid skinning.
- Storage life is 6 months after delivery.

The information contained herein is correct to the best of our knowledge. The recommendations or suggestions contained in this bulletin are made without guarantee or representation as to results. We suggest that you evaluate these recommendations and suggestions in your own laboratory prior to use. Our responsibility for claims arising from breach of warranty, negligence or otherwise is limited to the purchase price of the material.

PT. ETERNAL BUANA CHEMICAL INDUSTRIES
Tel. (62-21) 571 2998, Fax : (61-21) 571 2678

Issue date : Jan 10, 1996
Revised no : 01
Revised date : June 01, 2001