



## TECHNICAL DATA SHEET

### EBP - 2430 TL

#### I. DESCRIPTION

EBP - 2430 TL is low reactive, high viscosity, resilient, non-promoted ortho phthalic type unsaturated polyester resin with low peak exothermic.

#### II. PERFORMANCE

- Light color.
- Offers a quick gelation and slow cure.
- Flexible.

#### III. SUGGESTED USES

- For the manufacture of fancy buttons rod molding.

#### IV. SPECIFICATION

- Non-Volatile (150 °C, 3 hours) : 72 - 74 %
- Viscosity at 25 °C, cPs : 1,800 - 2,100  
(Brookfield LVT, No.3/60 rpm)
- Acid Value : maximum 18 mg KOH/g
- Color : colorless
- Appearance : clean/clear
- Gelling time at 25 °C, \* : 7 - 10 minutes

#### V. STANDARD PACKING

230 kgs in metal drum.

#### VI. STORAGE

- Storage life decreases with increasing temperature.
- Avoid exposure to heat source such as direct sunlight or steam pipes.
- Keep containers sealed to prevent moisture pick up and monomer loss.

\*) 0,5 % PT 2421 K, 1 % MEKPO

The information contained herein is correct to the best of our knowledge. The recommendations or suggestions contained in this bulletin are made without guarantee or representation as to results. We suggest that you evaluate these recommendations and suggestions in your own laboratory prior to use. Our responsibility for claims arising from breach of warranty, negligence or otherwise is limited to the purchase price of the material.

PT. ETERNAL BUANA CHEMICAL INDUSTRIES  
Phone (62-21) 571 2998, Fax (62- 21) 571 2678

Issue Date : April, 17, 2001  
Revised no : 2  
Revised date : August 10, 2009