



TECHNICAL DATA SHEET

EBP - 2504 I

I. DESCRIPTION

EBP - 2504 I is a medium reactive, pre-promoted special type unsaturated polyester resin.

II. PERFORMANCE

- Rigid, good mechanical properties.

III. SUGGESTED USES

- F R P molding products.

IV. SPECIFICATION

- Non-Volatile (105 °C, 3 hours) : 63 - 69 %
- Viscosity at 25 °C, cPs : 400 - 500
(Brookfield LVT, No.3/60 rpm)
- Acid Value : maximum 25 mg KOH/g
- Color : red violet
- Appearance : clean/clear – s. hazy
- Gelling time at 25 °C, (1 % MEKPO 50 %) : 14 - 21 minutes

V. STANDARD PACKING

230 kgs in metal drum.

VI. STORAGE

- Storage life decreases with increasing temperature.
- Avoid exposure to heat source such as direct sunlight or steam pipes.
- Keep containers sealed to prevent moisture pick up and monomer loss.

The information contained herein is correct to the best of our knowledge. The recommendations or suggestions contained in this bulletin are made without guarantee or representation as to results. We suggest that you evaluate these recommendations and suggestions in your own laboratory prior to use. Our responsibility for claims arising from breach of warranty, negligence or otherwise is limited to the purchase price of the material.